



**FIRE
TECHNOLOGY
SERVICES**

Confidential Report

Our Ref: 27/03015E/01/14

Notified Body
for PPE Directive,
Construction Products Directive
& Marine Equipment Directive
I.D. No. 0338 & 0339

**Fire Technology Services
A division of BTTG T & C Ltd
Wira House, West Park Ring Road,
Leeds, LS16 6QL**

Tel No: +44 (0)113 25919969 Fax No: +44 (0)113 2780306



**FIRE
TECHNOLOGY
SERVICES**

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

14 February 2014

Our Ref: 27/03015E/01/14
Your Ref:

Page 1 of 3

Client: Renner Italia S.P.A.
Via Ronchi Inferiore 34
40061 Minerbio
Italy

Job Title: **Fire Test on One Sample of Panels**

Clients Order Ref: --

Date of Receipt: 2 January 2014

Description of Sample: One sample of panels, referenced: No. 6 – White Matt

Specimen: MDF
Thickness: 20mm

Basecoat: FL0511
+FC1110 50% hardener
+DF---M005 20% thinner 2x150g/m²

Topcoat: F02510 clear converter
+EF---M060/--C02 25% inorganic pigmented paste
+FC1110 50% hardener
+DF---M005 20% thinner 1x120g/m²

Total Weight 420g/m²

Work Requested: Fire Technology Services were requested to carry out a fire test on the sample supplied to BS 476 Part 7 (Indicative).



14 February 2014

Page 2 of 3

Our Ref: 27/03015E/01/14
Your Ref:

Renner Italia S.P.A.

**FIRE TESTS ACCORDING TO BS 476:PART 7:1987 (AS AMENDED)
(Method for classification of the surface spread of flame of products) (Indicative)**

Date of Test: 13/02/14

Conditioning

The sample was conditioned to constant mass at a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 10\%$ and maintained in this condition until required for testing.

Procedure

The test was carried out in accordance with BS 476: Part 7: 1987. The sponsor sampled the material and the panel was cut from the sample to the dimensions set out in the standard by the sponser. The specimen was tested loose laid onto 12mm calcium silicate board
Only one specimen was tested. It should be noted that the above standard requires a minimum of six specimens to be tested.

The following were recorded:-

- a) the time at which the flame front crosses each vertical reference line;
- b) the maximum extent of flame spread during the first 1.5 min from the start of the test;
- c) the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- d) the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5min and the final flame spread results were compared with the standard class limits and a classification was assigned.

Requirements

The class limits for flamespread, detailed in BS 476:Part 7: are set out below.

	Flame spread at 1.5 min (mm)	Final flame spread (mm)
Class 1	165 (+25)	165 (+25)
Class 2	215 (+25)	455 (+45)
Class 3	265 (+25)	710 (+75)
Class 4	Exceeding Class 3 limits.	

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.



**FIRE
TECHNOLOGY
SERVICES**

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

14 February 2014

Page 3 of 3

Our Ref: 27/03015E/01/14
Your Ref:

Renner Italia S.P.A.

Results

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

<u>Time for flame spread to reach (s)</u> <u>(mm)</u>					<u>Flame spread</u> <u>at 1.5 min</u> <u>(mm)</u>	<u>Maximum</u> <u>flame spread</u> <u>(mm)</u>	<u>Time to reach</u> <u>maximum flame</u> <u>spread (s)</u>
165	215	265	455	710			
--	--	--	--	--	60	60	65

The results indicate that the sample met the performance requirements of Class 1 indicative.

Observations


--

Comments

Only one specimen was tested. No guarantee can be given as to the outcome of definitive testing. This report does not have the status of a full UKAS Accredited Test Certificate, therefore, it cannot be substituted or used as such.

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Reported by:  B Marsden (Mrs), Fire Technician

Countersigned by:  P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.